

Table 1. 2008 Preliminary Assay Results - Eau Claire Gold Deposit

Hole ID	From	To	Length (m)	Au g/t	Au oz/ton	Vein ID	Notes
ER08-113	113.8	114.3	0.50	20.90	0.61	T1	VQTL VG
	117.9	118.9	1.00	7.65	0.22	T1	
incl.	118.4	118.9	0.50	14.25	0.42	T1	
ER08-114	53.5	54.0	0.50	12.60	0.37	P	
ER08-115	58.4	58.9	0.50	17.85	0.52	JQ	VQTL VG
	69.5	70.1	0.60	40.80	1.19	R	VQTL VG
	150.6	151.1	0.50	12.95	0.38	T3	VQTL VG
ER08-116	58.6	60.1	1.50	38.31	1.12	JQ	VQTL VG
incl.	59.1	59.6	0.50	101.00	2.95		
	71.2	72.2	1.00	14.64	0.43	R	
ER08-117	58.5	59.5	1.00	120.20	3.51	JQ	VQTL VG
incl.	59.0	59.5	0.50	168.50	4.92		
	71.5	73.5	2.00	9.96	0.29	R	
incl.	72.5	73.0	0.50	27.10	0.79		VQTL VG
	106.7	107.2	0.50	27.00	0.79	T	VQTL VG
ER08-118	65.4	65.9	0.50	59.40	1.73	JQ	VQTL VG
	79.5	80.6	1.10	7.57	0.22	R	VQTL VG
	120.5	122.0	1.50	29.74	0.87	T	VQTL VG
incl.	120.5	121.0	0.50	39.50	1.15		
incl.	121.0	121.5	0.50	45.80	1.34		
ER08-120	114.6	115.6	1.00	6.76	0.20	S	
	208.6	209.1	0.50	9.64	0.28	T	
ER08-121	59.5	61.9	2.40	8.96	0.26	JQ	VQTL VG
incl.	61.4	61.9	0.50	17.80	0.52		
ER08-122	85.4	86.4	1.00	65.88	1.92	S	VQTL VG
incl.	85.9	86.4	0.50	129.00	3.77		
ER08-123	52.7	53.2	0.50	31.70	0.93	P	VQTL VG
	65.0	65.5	0.50	10.00	0.29	JQ	
	117.0	117.5	0.50	10.25	0.30	T	
ER08-126	74.9	75.4	0.50	22.00	0.64	JQ	
	88.2	89.2	1.00	11.36	0.33	R	VQTL VG
incl.	88.7	89.2	0.50	18.95	0.55		
ER08-128	117.4	118.9	1.50	12.89	0.38	P	
incl.	118.4	118.9	0.50	20.50	0.60		
ER08-129	121.5	122.0	0.50	41.30	1.21	JQ	VQTL VG
	244.0	245.0	1.00	17.76	0.52	T	
incl.	244.5	245.0	0.50	34.00	0.99		

Table 1. 2008 Preliminary Assay Results - Eau Claire Gold Deposit

Hole ID	From	To	Length (m)	Au g/t	Au oz/ton	Vein ID	Notes
ER08-130	51.0	52.5	1.50	7.44	0.22	P	
	61.4	61.9	0.50	9.37	0.27	JQ	
	93.8	94.8	1.00	35.70	1.04	S	
ER08-131	58.2	59.7	1.50	37.45	1.09	JQ	
	incl. 58.7	59.2	0.50	67.50	1.97		VQTL VG
ER08-132	73.5	74.5	1.00	35.55	1.04	JQ	VQTL VG
	incl. 74.0	74.5	0.50	49.30	1.44		
	84.0	84.5	0.50	12.60	0.37	R	
	122.1	123.1	1.00	74.15	2.17	T	
	incl. 122.6	123.1	0.50	147.10	4.30		VQTL VG
	159.5	164.5	5.00	8.42	0.25	T3	
incl. 161.0	161.5	0.50	57.60	1.68			
Eau Claire Gold deposit - Average composite gold grades							
Cut off grade		Number of	Length	Average Grade			
Au g/t		Intercepts	m	Au g/t	Au oz/ton		
0		80	1.05	13.16	0.38		
4.6		51	1.01	18.66	0.54		
7.5		39	0.85	25.82	0.75		
10		26	0.85	34.32	1.00		

Chemical analysis was completed by ALS CHEMEX Laboratories using a 50-gram split and gravimetric techniques. The visible gold samples were mechanically screened and assayed for metallics. Internal standards provided by an independent company and blank samples were inserted for quality control purposes.

Note: Sample length approximates true thickness. VQTL VG - Quartz-tourmaline vein with visible gold. Assay results are pending for an additional 44 drill holes.